


ProLine 130

Multi-layer, durable roof and facade membrane. Driving rain proof. Open to diffusion. Time saving through integrated self-adhesive seam. Can be used from DN >15°.



application	roof membrane windproof and rainproof facade membrane for closed facades		
functional layer	microporous functional film		
carrier material	polypropylene fleece		
color	grey		
basis weight	EN 1849-2	g/m ²	130 (±10)

PROPERTY	TEST	UNIT	VALUE
----------	------	------	-------

General characteristics

roll width	EN 1848-2	m	1,5
roll length	EN 1848-2	m	25 50
m ² per roll	EN 1848-2	m ²	37,5 75
weight roll	-	kg	5 10

Technical characteristics

behavior in case of fire	EN 13501-1	Class	E
resistance to water penetration	EN 1928	Class	W1
after artificial aging	EN 1297/1296	Class	W1
maximum tensile force MD/CD	EN 12311-1	N / 50mm	305/180
maximum tensile strength after aging MD/CD	EN 12311-1	%	60/50
elongation MD/CD	EN 12311-1	%	65/65
elongation after aging MD/CD	EN 1297/1296	%	43/49
tear resistance / nail shaft MD/CD	EN 12310-1	N / 200mm	150/140
cold bending behavior	EN 1109	°C	-40
sd value	EN ISO 12572	m	0,02
resistance to air passage	EN 12114	m ³ /(m ² /h/50Pa)	<0,01
temperature resistance	EN 13859-1	°C	-40 to +80
UV resistance	-	month	1
suitability as a material for temporary cover	-	month	1
ZVDH product data sheet - class	-	-	UDB-A / USB-A
Ö-Norm: B3661 – Table 5/4119 – Section 6.1.2	-	-	Type I

These values may have tolerances. Unless otherwise stated, industry standard, material and performance tolerances apply.